

TEST REPORT

Number: HPFJ012825

Applicant: LACROSSE FOOTWEAR INC.
18550 NE RIVERSIDE
PARKINGWAY PORTLAND,
OREGON 97230 USA

Date: Aug 01, 2006

Attn: GRANT HUNTER/CHRIS WOJNAR

Sample Description:

One (1) pair of submitted sample said to be Arrow outsole#QUAD sole in Transparent.


Standard : ASTM
Buyer's Name : Lacrosse Footwear Inc.
Date Received/Date Test Started : July 26, 2006

Conclusion:

Oil Resistance M
Mark II Slip Resistance F

Note : M = Meet client's requirement F = Below client's requirement
= No specified requirement N/A = Not applicable

AUTHORIZED BY:
FOR INTERTEK TESTING SERVICES
SHENZHEN LTD.



HUANG NING, ANDY
MANAGER

baron / dengwh

TEST REPORT

Number: HPFJ012825

Tests Conducted (As Requested By The Applicant)

1 Oil Resistance (ASTM D471: 1998, 903 Oil X 22 Hours):

		<u>Client's</u>
		<u>Requirement</u>
Volume Swell:	-4.4 %	Max. 10 %

2 Mark II Slip Resistance (ASTM F1677: 1996, Olean Red Quarry Tile):

		<u>Client's</u>
		<u>Requirement</u>
Dry:	0.56	Min. 0.50
Wet:	0.31	
