

TEST REPORT

Number: HPFJ012820

Applicant: LACROSSE FOOTWEAR INC.
18550 NE RIVERSIDE
PARKINGWAY PORTLAND,
OREGON 97230 USA

Date: Aug 01, 2006

Attn: GRANT HUNTER/CHRIS WOJNAR

Sample Description:

One (1) pair of submitted sample said to be Quantum Rubber outsole#LWF sole in Black/Yellow.

Standard : ASTM

Buyer's Name : Lacrosse Footwear Inc.

Date Received/Date Test Started : July 26, 2006

Conclusion:


Oil Resistance M

Slip Resistance M

Note : M = Meet client's requirement F = Below client's requirement

= No specified requirement N/A = Not applicable

AUTHORIZED BY:
FOR INTERTEK TESTING SERVICES
SHENZHEN LTD.



HUANG NING, ANDY
MANAGER

baron / dengwh

Page 1 Of 2

Intertek Testing Services Shenzhen Ltd.Guangzhou GDD Branch

深圳天祥质量技术服务有限公司广州开发区分公司

3/F., Hengyun Building, 728 Xiagang Ave., Guangzhou

Economic & Technological Development District, Guangzhou

广州经济技术开发区开发大道728号恒运大厦3楼

Tel# 86-020-2232 1668/8396 6868 Fax: 020-82089909

TEST REPORT

Number: HPFJ012820

Tests Conducted (As Requested By The Applicant)

1 Oil Resistance (ASTM D471: 1998, 903 Oil X 22 Hours):

		<u>Client's Requirement</u>
	Black	
Volume Swell:	9.5 %	Max. 10 %

2 Mark II Slip Resistance (ASTM F1677: 1996, Olean Red Quarry Tile):

		<u>Client's Requirement</u>
Dry:	0.94	Min 0.50
Wet:	0.64	
